Technical Data Sheet





Technical Data

Solvent	Hydrocarbon
Propellant	Hydrocarbon
Solids content (approx.)	30%
Spray pattern	Web
Colour	Clear
Coverage (approx.)	100m ²
VOC	548 g/l
Heat Resistance	90°C
Open time	Up to 120 min.
Drying time	1-2 min.
Shelf life	12 months
Storage temperature	15°C - 35°C

DASA DS-408 Canister

Features

- Methylene chloride free
- Uniform spray
- Fast easy application
- Fast drying
- High solids
- High temperature resistance
- Low odour
- Long open time
- Bonds a wide variety of substrates

Properties & application

- Bonds a wide variety of substrates, including wood, metals, rubber, fabric, most plastics, cardboard, polythene and concrete, as well as decorative laminates.
- Ideal for permanent bonds that require good initial bond strength. It provides good temperature resistance and if protected from contamination has an open time of several hours.
- Always test a small sample of the materials first to ensure the suitability of the product for the application. For instance, some vinyls contain large amounts of plasticiser which, over time, can migrate and soften the bond. When in doubt, test first.

DO NOT USE ON FLEXIBLE PVC OR EXPANDED POLYSTYRENE.

Directions for use

- Surfaces should be clean, dry and free from grease, oil and dust. Excessive dust will impair performance.
- Attach a suitable spray nozzle, such as a Unijet 9501, to the spray gun.
- Connect the hose to the canister and the spray gun to the hose and tighten the connections.
- 4. Open the valve on the canister. The valve should remain open until the canister is used up. Use the locking nut on the gun after use. Turning off the valve will result in the adhesive drying in the hose and gun causing blockages.
- 5. Hold the spray gun at 90° to the surface and apply a uniform coat of adhesive, to both substrates, ensuring 90-100% coverage. Spray one surface vertically the other horizontally. Pay particular attention to the edges.
- Allow the adhesive to tack up and protect from contamination whilst this happens. The adhesive is ready to bond when it feels dry to the touch and does not transfer.

Limitations

DS-408 dries in two minutes under normal conditions, but this will vary under different temperatures and humidities. High humidity and low temperatures will slow the drying time and if the temperature gets very low, can produce bloom. Bloom is moisture which forms on the glue line caused by solvent evaporation lowering the air temperature above it.

- 7. Porous substrates may require two applications
- Drying takes approximately 1 to 2 minutes depending on substrates, ambient temperature and humidity. Over spraying and pooling of the adhesive will increase the drying time.
- **9.** After spraying, remove the spray gun tip and rinse with Solvent Cleaner before it has cured.
- It is important to remember that DASA DS-408 is a contact adhesive and forms a bond by sticking to itself, so there must be sufficient adhesive on both surfaces for this to happen.
- Once the two surfaces have been brought together, and aggressive bond will be made.
- 12. Apply a uniform pressure over the work piece, starting in the middle and working outwards, to ensure full contact. Pay particular attention to the edges. A roller will give the best results. Full cure will take 24 hours.

Storage

Protect from extremes of temperature in a controlled environment between 15 and 35°C, and away from direct sunlight. Do not stand on a cold concrete floor. Low temperatures can result in irreparable separation of the adhesive. Stored under the correct conditions, in original, unopened containers, the product will have a shelf life of 12 months.

DO NOT ALLOW THE PRODUCT TO FREEZE

Disclaimer

All the information in the Data Sheet is based on practical experience and is published in good faith. However, because we have no control over the manner or conditions in which our products are used, or over work undertaken or end product manufactured by the purchaser, we cannot accept liability for results. Responsibility for ascertaining the suitability of products for his purposes rests with the purchaser. All conditions, representations, statements, warranties or guarantees whatsoever, whether express, implied orstatutory, in respect of any goods manufactured, sold or supplied by us are hereby expressly excluded and we accept no liability in respect of any claim for damage or consequential loss caused to any property arising directly or indirectly out of the use of our products or goods.

DASA International B.V. Bergerweg 62-M 1815 AE Alkmaar The Netherlands

Tel: +31 72 571 99 17 Mail: info@dasa-international.com Web: www.dasa-international.com

© 2023 DASA International B.V. Version 202307V1 All rights reserved. This publication or any portion thereof may not be reproduced or used in any manner whatsoever without the express written permission of the publisher