



Technical Data

Solvent	Hydrocarbon Acetone Ether Toluene
Propellant	Ether
Solids content (approx.)	35%
Spray pattern	Web
Colour	Green
Coverage (approx.)	150m ²
VOC	589 g/l
Heat Resistance	90°C
Open time	Up to 60 min.
Drying time	2-5 min.
Shelf life	12 months
Storage temperature	15°C - 35°C

DASA DS-708 Canister

Features

- Uniform spray
- Fast easy application
- Fast drying
- High solids
- High temperature resistance
- Non-chlorinated
- Long open time
- Bonds to a wide variety of substrates

Properties & application

- A non-chlorinated, high solids content, sprayable canister adhesive with excellent grab and long open time.
- Designed for bonding EPDM rubber to various substrates including MDF, chipboard, plywood, OSB board and other timber sheet materials as well as insulation board, concrete, masonry, brick and most metals.
- Always test a small sample of the materials first to ensure the suitability of the product for the application.

DO NOT USE ON FLEXIBLE PVC OR EXPANDED POLYSTYRENE.

Directions for use

1. Ensure roof surface is clean, dry and free of standing water. Any standing water should be removed and the surface left to dry for at least 1 hour before applying adhesive.
2. Attach a suitable spray nozzle, such as a Unijet 9501, to the spray gun. Use a spray gun with a 600mm extension so that the adhesive can be applied whilst standing.
3. Connect the hose to the canister and the spray gun to the hose and tighten the connections.
4. Open the valve on the canister. The valve should remain open until the canister is used up. Use the locking nut on the gun after use. Turning off the valve will result in the adhesive drying in the hose and gun causing blockages.
5. Ensure membrane is cut to size and ready to bond.
6. Hold the spray gun at 90° to the surface and apply a uniform coat of adhesive to both substrates, ensuring 80-100% coverage. Spray one surface vertically the other horizontally. It is important to remember that **DASA DS-708** is a contact adhesive and forms a bond by sticking to itself, so there must be sufficient adhesive on both surfaces for this to happen.
7. Do not allow the adhesive to puddle.
8. Take care not to apply **DASA DS-708** to the seaming areas.
9. Allow solvent to evaporate so that the adhesive is dry to the touch before laying membrane in position. Drying takes approximately two to five minutes depending on substrates, ambient temperature and humidity. Over spraying and pooling of the adhesive will increase drying time.
10. Apply pressure to the surface with a broom or roller to ensure full contact.
11. After spraying, remove the spray gun tip and rinse with a suitable solvent cleaner before it has cured.

Limitations

DASA DS-708 dries in two to five minutes under normal conditions, but this will vary under different temperatures and humidities. High humidity and low temperatures will slow the drying time and if the temperature gets very low, can produce bloom. Bloom is moisture which forms on the glue line caused by solvent evaporation lowering the air temperature above it.

Storage

Protect from extremes of temperature in a controlled environment between 15 and 35°C, and away from direct sunlight. **Do not stand on a cold concrete floor.** Low temperatures can result in irreparable separation of the adhesive. Stored under the correct conditions, in original, unopened containers, the product will have a shelf life of 12 months.

DO NOT ALLOW THE PRODUCT TO FREEZE

Disclaimer

All the information in the Data Sheet is based on practical experience and is published in good faith. However, because we have no control over the manner or conditions in which our products are used, or over work undertaken or end product manufactured by the purchaser, we cannot accept liability for results. Responsibility for ascertaining the suitability of products for his purposes rests with the purchaser. All conditions, representations, statements, warranties or guarantees whatsoever, whether express, implied or statutory, in respect of any goods manufactured, sold or supplied by us are hereby expressly excluded and we accept no liability in respect of any claim for damage or consequential loss caused to any property arising directly or indirectly out of the use of our products or goods.

DASA International B.V.

Bergerweg 62-M
1815 AE Alkmaar
The Netherlands

Tel: +31 72 571 99 17
Mail: info@dasa-international.com
Web: www.dasa-international.com

© 2023 DASA International B.V. Version 202307V1

All rights reserved. This publication or any portion thereof may not be reproduced or used in any manner whatsoever without the express written permission of the publisher.