



Technical Data

Solvent	Acetone Cyclohexane
Propellant	Dimethylether
Solids content (approx.)	40%
Spray pattern	Web
Colour	Green
Coverage (approx.)	6m ²
VOC	590 g/l
Heat Resistance	-40 to +130°C
Open time	Up to 60 min.
Drying time	3-4 min.
Shelf life	12 months
Storage temperature	15°C - 35°C

DASA DS-702 Aerosol

Features

- Toluene free
- Non-chlorinated
- Uniform spray
- Fast easy application
- Fast drying
- High solids
- High temperature resistance
- Long open time

Properties & application

- A non-chlorinated, toluene free, high solids content, sprayable canister adhesive with excellent grab and long open time.
- Designed for bonding EPDM rubber to various substrates including MDF, chipboard, plywood, OSB board and other timber sheet materials as well as insulation board, concrete, masonry, brick and most metals.
- Always test a small sample of the materials first to ensure the suitability of the product for the application.

**DO NOT USE ON FLEXIBLE PVC OR
EXPANDED POLYSTYRENE.**

Directions for use

1. Ensure roof surface is clean, dry and free of standing water. Any standing water should be removed and the surface left to dry for at least 1 hour before applying adhesive.
 2. Shake can well before use.
 3. Ensure membrane is cut to size and ready to bond.
 4. Hold the aerosol at approximately 90° to the surface and apply a uniform coat of adhesive to both substrates, ensuring 80-100% coverage. Spray one surface vertically the other horizontally.
 5. Do not allow the adhesive to puddle.
 6. Take care not to apply **DASA DS-702** to the seaming areas.
 7. Allow solvent to evaporate so that the adhesive is dry to the touch before laying membrane in position. Drying takes approximately two to five minutes depending on substrates, ambient temperature and humidity.
 8. Apply pressure to the surface with a broom or roller to ensure full contact.
 9. After spraying, invert can and spray until nozzle is clear of adhesive.
- Over spraying and pooling of the adhesive will increase drying time.

Limitations

DS-702 dries in three to four minutes under normal conditions, but this will vary under different temperatures and humidities. High humidity and low temperatures will slow the drying time and if the temperature gets very low, can produce bloom. Bloom is moisture which forms on the glue line caused by solvent evaporation lowering the air temperature above it.

Storage

Protect from extremes of temperature in a controlled environment between 15 and 35°C, and away from direct sunlight. Do not stand on a cold concrete floor. Low temperatures can result in irreparable separation of the adhesive. Stored under the correct conditions, in original, unopened containers, the product will have a shelf life of 12 months.

DO NOT ALLOW THE PRODUCT TO FREEZE

Disclaimer

All the information in the Data Sheet is based on practical experience and is published in good faith. However, because we have no control over the manner or conditions in which our products are used, or over work undertaken or end product manufactured by the purchaser, we cannot accept liability for results. Responsibility for ascertaining the suitability of products for his purposes rests with the purchaser. All conditions, representations, statements, warranties or guarantees whatsoever, whether express, implied or statutory, in respect of any goods manufactured, sold or supplied by us are hereby expressly excluded and we accept no liability in respect of any claim for damage or consequential loss caused to any property arising directly or indirectly out of the use of our products or goods.

DASA International B.V.

Bergerweg 62-M
1815 AE Alkmaar
The Netherlands

Tel: +31 72 571 99 17
Mail: info@dasa-international.com
Web: www.dasa-international.com

© 2023 DASA International B.V. Version 202307V1
All rights reserved. This publication or any portion thereof may not be reproduced or used in any manner whatsoever without the express written permission of the publisher.